



Textiles — Tests for colour fastness — Part J02: Instrumental assessment of relative whiteness

TECHNICAL CORRIGENDUM 1

Textiles — Essais de solidité des teintures —

Partie J02: Évaluation instrumentale de la blancheur relative

RECTIFICATIF TECHNIQUE 1

Technical Corrigendum 1 to International Standard ISO 105-J02:1997 was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 1, *Tests for coloured textiles and colorants*.

Page 6

8.2 NOTES 1 and 2:

- 1 3rd sentence should read: "The higher the value of W or W_{10} , the greater the whiteness.
4th sentence should read: "Equal differences in W or W_{10} values do not necessarily indicate equal differences in perceived whiteness or equal concentration differences of FWA. Similarly, equal differences in T_w or $T_{w,10}$ values do not always represent equal perceptual differences in greenishness or reddishness of whites."
- 2 The whiteness index is only applicable for specimens whose values of W and T_w (for both 2° and 10° observers) lie within the following limits:
Limited to: $40 < W < 5Y - 280$
Limited to: $-3 < T_w < +3$

Pour plus d'infos, merci de nous contacter.

Association Sénégalaise de Normalisation

4 Avenue Jean Jaurès, Immeuble El Hadj Omar DIA, 6 ème Etage
Dakar - SENEGAL

Tel: +221 33 829 58 25

Email: asn@asn.sn